

E.Miroglio EAD  
 ISO 14001:2015  
 Cert. N°0039338  
 ISO 9001:2015  
 Cert. N°0039339



SAFE &  
 healthy  
 working  
 conditions



NO harmful  
 or irritant  
 chemicals  
 used

### **impiego**

macchina rettilinea su finezza 12-14 ad 1 filo, circolare da 12 a 20 ad 1 filo.

### **estensibilità e restringimento**

il grado d'elasticità del capo è determinato dalla regolazione della tensione del filo e della fittezza dei punti maglia in fase di smacchinatura. Si consiglia di eseguire un capo prototipo e sottoporlo ad un test di lavaggio.

### **scarto di lavorazione**

la particolare costruzione di quest'articolo e il processo di tintura comportano uno scarto del 5-7%.

### **colori**

uniti

### **solidità**

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

### **finissaggio industriale**

per scaricare le tensioni di lavorazione e completare il ritorno elastico della componente poliestere, si consiglia di lavare con ammorbidente specifico e vaporizzare abbondantemente in fase di stiro.

### **servizio campionature fino al 30-06-2019**

\* colori pronti per campionatura

per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.

90% VI viscosa / viscose  
 10% PL poliestere elasticizzato / stretch polyester

### **use**

*flat-knitting machine gauge 12-14 for 1-ply, circular from 12 to 20 for 1-ply.*

### **stretch and shrinking degree**

*the garment stretch degree is determined by yarn tension and knit thickness adjustment during knitting. It is suggested to make a prototype garment and wash it as a test.*

### **knitting waste**

*the particular yarn construction and dyeing process may cause a 5-7% knitting waste.*

### **colours**

*solid*

### **fastness**

*in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.*

### **industrial finishing**

*in order to loosen the knitting tensions and help the polyester component stretch return, it is suggested to wash with specific softener and steam generously during ironing.*

### **sampling service until 30-06-2019**

*\* colours ready for sampling*

*for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.*

- 1 bianco white
- 2 chiari light
- 3 medi medium
- 4 scuri dark
- 5 special special

