



by EDOARDO MIROGLIO

E.Miroglia EAD
 ISO 14001:2015
 Cert. N°0039338
 ISO 9001:2015
 Cert. N°0039339

SAFE &
healthy
working
conditionsNO harmful
or irritant
chemicals
used**impiego**

macchina rettilinea su finezza 12-14 a 1 filo, circolare da 12 a 20 a 1 filo, cotton 21-24-27 gauge a 1 filo.
 Per valutare i cali nei vari punti maglia, è necessario eseguire un capo prototipo e sottoporlo a test di lavaggio. In fase di smacchinatura, porre particolare attenzione alla messa a punto della macchina, per limitare le rotture della piattina di poliestere.
 Per ottenere una superficie uniforme nei colori YT1, YVI, VD4, VD5, V41, YAJ e ZWD si consiglia di lavorare il filato a più guidafili.

scarto di lavorazione

la particolare costruzione di questo articolo e il processo di tintura comportano uno scarto del 3%.

colori

uniti

solidità

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

finissaggio industriale

vaporizzare abbondantemente in fase di stiro; per una mano più fluida e per eliminare le tensioni di smacchinatura, si consiglia un lavaggio con ammorbidente specifico.

Tutti i colori sono pronti a [Stock Service](#)

per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.

80% VI rayon viscosa / viscose rayon
 10% fibra metalizzata / metallized fibre
 10% PA fibra poliammidica / polyamide fibre

use

*flat-knitting machine gauge 12-14 for 1-ply, circular from 12 to 20 for 1-ply, cotton 21-24-27 gauge for 1-ply.
 Make and wash a prototype garment to evaluate shrinkage in the different knits.
 Pay great attention during knitting to the set-up of the machine, in order to limit the polyester breakage.
 When knitting YT1, YVI, VD4, VD5, V41, YAJ and ZWD colors, it's advisable to use several threadguides to obtain a more uniform surface.*

knitting waste

the particular yarn construction and dyeing process cause a 3% knitting waste.

colours

solid

fastness

in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.

industrial finishing

steam generously during ironing; for a smoother hand and to eliminate the shrinkage due to the knitting tensions, it is suggested to wash with specific softener.

All colours are ready on [Stock Service](#)

for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.

