



by EDUARDO MIROGLIO

E.Miroglio EAD  
ISO 14001:2015  
Cert. N° BG.121922E/U  
ISO 9001:2015  
Cert. N° BG.121922Q/U



SAFE &  
healthy  
working  
conditions



NO harmful  
or irritant  
chemicals  
used

### impiego

macchina rettilinea su finezza 16 e 14 a 1 filo, cotton  
24-27 gauge a 1 filo.

### estensibilità e restringimento

il grado d'elasticità del capo è determinato dalla regolazio-  
ne della tensione del filo e della fittezza dei punti maglia  
in fase di smacchinatura. Si consiglia di eseguire un capo  
prototipo e sottoporlo ad un test di lavaggio.

### scarto di lavorazione

la particolare costruzione di questo articolo e il processo di  
tintura comportano uno scarto del 5-7%.

### colori

uniti

### solidità

secondo le norme UNI/ISO; per i rigati con colori  
contrastanti, è necessario richiedere solidità specifiche  
ed eseguire test di lavaggio.

### finissaggio industriale

per scaricare le tensioni di lavorazione e completare il  
ritorno elastico della componente poliammidica si consiglia  
di lavare con ammorbidente specifico e vaporizzare abbon-  
dantemente in fase di stiro.

### servizio campionature fino al 30-06-2024

\* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo e dei bagni  
ottimali di tintura, vi preghiamo di richiedere la  
scheda tecnica.*

### use

flat-knitting machine gauge 16-14 for 1-ply, cotton  
24-27 gauge for 1-ply.

### stretch and shrinking degree

the garment stretch degree is determined by yarn tension  
and knit thickness adjustment during knitting. It is sug-  
gested to make a prototype garment and wash it as a test.

### knitting waste

the particular yarn construction and dyeing process cause  
a 5-7% knitting waste.

### colours

solid

### fastness

in compliance with UNI/ISO norms; for striped garments  
with contrasting colours, it is recommended to ask for  
specific fastness and carry out washing tests.

### industrial finishing

in order to loosen the knitting tensions and help the  
polyamide component stretch return, it is suggested to  
wash with specific softener and steam generously during  
ironing.

### sampling service until 30-06-2024

\* colours ready for sampling

*for any information regarding the use and dye-lot  
sizes of the yarn please ask for the technical sheet.*

•1 bianco *white* •2 chiari *light* •3 medi *medium* •4 scuri *dark* •5 special *special*

