



65% VI viscosa FSC® / FSC® viscose
26% WO lana Merino extrafine irrestingibile /
shrink-resistant extrafine Merino wool
9% PA poliammide / polyamide

W
25
26

by EDOARDO MIROGLIO

E.Miroglio EAD

ISO 14001:2015

Cert. N° BG.121922E/U

ISO 9001:2015

Cert. N° BG.121922Q/U

SAFE &
healthy
working
conditionsNO harmful
or irritant
chemicals
used**impiego**

macchina rettilinea su finezza 14 a 1 filo, 12 a 2 fili, circolare da 12 a 20 a 1 filo, cotton 24-27 gauge a 1 filo.

colori

uniti e mélange.

solidità

secondo le norme UNI/ISO; per i rigati con colori contrastanti, è necessario richiedere solidità specifiche ed eseguire test di lavaggio.

finissaggio industriale

vaporizzare abbondantemente in fase di stiro. Per ottenere una mano più gonfia e quindi una maglia più curata, è consigliabile un lavaggio con un minimo di ammorbidente specifico.

servizio campionature fino al 31-12-2024

* colori pronti per campionatura

per informazioni sull'utilizzo dell'articolo e dei bagni ottimali di tintura, vi preghiamo di richiedere la scheda tecnica.

use

flat-knitting machine gauge 14 for 1-ply, 12 for 2 ply, circular from 12 to 20 for 1-ply, cotton 24-27 gauge for 1-ply.

colours

solid and mélange.

fastness

in compliance with UNI/ISO norms; for striped garments with contrasting colours, it is recommended to ask for specific fastness and carry out washing tests.

industrial finishing

steam generously during ironing. Wash with a minimum dose of appropriate softener for a more voluminous touch and a cleaner feel.

sampling service until 31-12-2024

* colours ready for sampling

for any information regarding the use and dye-lot sizes of the yarn please ask for the technical sheet.

•1 bianco *white* •2 chiari *light* •3 medi *medium* •4 scuri *dark* •5 special *special*

