



85% VI viscosa FSC® / FSC® viscose
15% PL poliestere elasticizzato / stretch polyester

W
25
26

by EDOARDO MIROGLIO

E.Miroglio EAD
ISO 14001:2015
Cert. N° BG.121922E/U
ISO 9001:2015
Cert. N° BG.121922Q/U



SAFE &
healthy
working
conditions



NO harmful
or irritant
chemicals
used

impiego

macchina rettilinea su finezza 16-14 a 1 filo, 12 a 2 fili,
circolare da 16 a 20 a 1 filo.

estensibilità e restringimento

il grado d'elasticità del capo è determinato dalla regolazio-
ne della tensione del filo e della fittezza dei punti maglia
in fase di smacchinatura. Si consiglia di eseguire un capo
prototipo e sottoporlo ad un test di lavaggio.

scarto di lavorazione

la particolare costruzione di quest'articolo e il processo di
tintura comportano uno scarto del 5-7%.

colori

uniti

solidità

secondo le norme UNI/ISO; per i rigati con colori
contrastanti, è necessario richiedere solidità specifiche
ed eseguire test di lavaggio.

finissaggio industriale

per scaricare le tensioni di lavorazione e completare il
ritorno elastico della componente poliestere, si consiglia di
lavare con ammorbidente specifico e vaporizzare abbon-
dantemente in fase di stiro.

servizio campionature fino al 31-12-2024

* colori pronti per campionatura

*per informazioni sull'utilizzo dell'articolo e dei bagni
ottimali di tintura, vi preghiamo di richiedere la
scheda tecnica.*

use

*flat-knitting machine gauge 16-14 for 1-ply, 12 for 2 ply,
circular from 16 to 20 for 1-ply*

stretch and shrinking degree

*the garment stretch degree is determined by yarn tension
and knit thickness adjustment during knitting. It is sugge-
sted to make a prototype garment and wash it as a test.*

knitting waste

*the particular yarn construction and dyeing process may
cause a 5-7% knitting waste.*

colours

solid

fastness

*in compliance with UNI/ISO norms; for striped garments
with contrasting colours, it is recommended to ask for
specific fastness and carry out washing tests.*

industrial finishing

*in order to loosen the knitting tensions and help the
polyester component stretch return, it is suggested
to wash with specific softener and steam generously
during ironing.*

sampling service until 31-12-2024

* colours ready for sampling

*for any information regarding the use and dye-lot
sizes of the yarn please ask for the technical sheet.*

•1 bianco *white* •2 chiari *light* •3 medi *medium* •4 scuri *dark* •5 special *special*

