



65% VI viscosa FSC® / FSC® viscose
 26% WO lana Merino extrafine irrestingibile /
 shrink-resistant extrafine Merino wool
 9% PA poliammide / polyamide

W
26
27

E.Miroglio EAD
 ISO 14001:2015
 Cert. N° BG003661
 ISO 9001:2015
 Cert. N° BG003660



SAFE &
 healthy
 working
 conditions



NO harmful
 or irritant
 chemicals
 used

impiego

macchina rettilinea su finezza 12-14 a 1 filo, 7 a 2-3 fili,
 circolare da 12 a 20 a 1 filo, cotton 21-24 gauge a 1 filo.

colori

uniti e mélange.

solidità

secondo le norme UNI/ISO; per i rigati con colori
 contrastanti, è necessario richiedere solidità specifiche
 ed eseguire test di lavaggio.

finissaggio industriale

vaporizzare abbondantemente in fase di stiro.
 Per ottenere una mano più gonfia e quindi una maglia
 più curata, è consigliabile un lavaggio con un minimo di
 ammorbidente specifico.

*per informazioni sull'utilizzo dell'articolo e dei bagni
 ottimali di tintura, vi preghiamo di richiedere la
 scheda tecnica.*

use

*flat-knitting machine gauge 12-14 for 1-ply, 7 for 2 or 3 ply,
 circular from 12 to 20 for 1 ply, cotton 21-24 gauge for 1 ply.*

colours

solid and mélange.

fastness

*in compliance with UNI/ISO norms; for striped garments
 with contrasting colours, it is recommended to ask for
 specific fastness and carry out washing tests.*

industrial finishing

*steam generously during ironing.
 Wash with a minimum dose of appropriate softener for a
 more voluminous touch and a cleaner feel.*

*for any information regarding the use and dye-lot
 sizes of the yarn please ask for the technical sheet.*

•1 bianco *white* •2 chiari *light* •3 medi *medium* •4 scuri *dark* •5 special *special*

